


## REMARKS

A Substitute Specification and Abstract is submitted herewith to place the case in better English form. The Substitute Specification and Abstract contains no new matter. In order that the examiner can satisfy himself in this regard, also submitted herewith is a marked-up copy of the original Specification and Abstract from which the Substitute Specification and Abstract was typed.

Respectfully submitted,

A handwritten signature in black ink, appearing to read "George A. Loud", is written over the typed name and registration number.

George A. Loud  
Reg. No. 25,814

Dated: May 5, 2005

LORUSSO & LOUD  
3137 Mt. Vernon Avenue  
Alexandria, VA 22305

(703) 739-9393

10 5 MAY 2005

## DESCRIPTION

Activation Energy Ray Sensitive Resin Composition,  
Activation Energy Ray Sensitive Resin Film and  
Method for Forming Pattern Using the Film

5

## Technical Field:

[0001] This invention relates to an activation energy ray-sensitive resin composition which <sup>contains</sup> ~~comprises~~ an acid former <sup>which</sup> ~~generating~~ <sup>is</sup> an acid by the action of activation <sup>radiation</sup> ~~energy rays~~ and <sup>which is</sup> dispersed in an aqueous solution of a water-soluble resin in the presence or absence of a sensitizer, to which an acid-reactive insolubilizing agent is added. <sup>The invention further relates</sup> to an activation energy ray-sensitive resin film obtainable from the above composition, and to a method for  
15 forming a pattern using the film.

## Background Art:

[0002] An activation energy ray-sensitive resin or resin composition is utilized for ~~a~~ covering ~~treatment etc.~~ <sup>this resin</sup> ~~by utilizing~~ <sup>undergoes a</sup> change in chemical structure created by the action of activation energy rays such as light, infrared rays, far-infrared rays, electron beams or X-rays. Among <sup>these</sup> ~~activation~~ <sup>energy forms</sup> ~~rays~~, light is widely used. For this reason, the  
25 following descriptions occasionally specifically refer<sup>s</sup> to light as the activation energy ~~rays~~. However, the activation energy ~~rays~~ <sup>with</sup> utilized in the composition and films ~~obtainable from the composition~~ according to the present invention <sup>is</sup> ~~are~~ not limited to light.

[0003] Resins or ~~compositions thereof~~ <sup>and compositions containing same</sup> which are sensitive to light are utilized in many fields and in large quantities as pattern forming materials having high resolution in photolithography ~~technology~~, etc. (see "Photopolymer Technology", edited by YAMAOKA, Tsuguo and  
35 MATSUNAGA, Gentaro, Nikkan Kogyo Shimbun Ltd. (1988))

Polymer-type photosensitive materials, which not only have good resolution but also <sup>provide</sup> permit setting of a wide range for a photosensitive region <sup>for use with a set</sup> by selecting the wavelengths of light, ~~are utilizable depending upon their intended~~ applications. Further, they have an important role in <sup>utility as</sup> that the resin layer <sup>which can be</sup> thereof patterned by irradiation with light <sup>and can thereby</sup> serves to function as a resist material in the case of a chemical, physical or mechanical etching ~~treatment~~ of the substrate. Further, they are actually used as a

10 platemaking material for letterpress printing, intaglio printing, lithography or stencil printing. By virtue of these characteristics, they are utilized as photolithography <sup>IC</sup> ~~process~~ materials encompassing a wide range from submicrons to centimeters.

15 [0004] In the case of a polymer-type photosensitive resin, patterns are formed through a development treatment which utilizes a change in <sup>a</sup> physical properties, such as solubility, caused as a result of a change in chemical structure in the exposed or unexposed region. When the

20 resin is used as a ~~material for a surface covering treatment~~, a change in chemical structure caused by light exposure induces a significant change in <sup>a</sup> physical property thereof ~~to provide for~~ <sup>to provide for</sup> to express the function of protection of a substrate. Such a change in chemical structure of the <sup>a number</sup>

25 resin is not attributed to the photochemical reaction alone; <sup>the combined effect</sup> Rather, the change is based on a total of chemical reactions, inclusive of various secondary reactions induced by the photochemical reaction. Thus, for example, it is possible to arbitrarily select the solubility of a resin

30 layer in a solvent before and after light exposure. Namely, when the solubility of the exposed region decreases, the resin serves as a negative-type photosensitive resin <sup>in</sup> ~~by a solvent developing treatment~~. When the solubility of the exposed area is <sup>increased</sup> improved, then

35 the resin serves as a positive-type photosensitive resin.

[0005] When patterning is effected by ~~the~~ development with a solvent, it is indispensable to use water as a solvent which is cheapest and safest, since it is directly related to environmental problems including work  
5 environment and waste treatment. When water which is neutral and which has high polarity is used as a solvent, it is required that the material to be dissolved therein should ~~be~~ <sup>have a degree of</sup> also high in polarity. Therefore, examples of photosensitive resin capable of being developed with  
10 neutral water are restricted as will be described hereinafter.

[0006] From the foregoing viewpoint, the production of photosensitive films <sup>which can be developed</sup> using neutral water by itself as a solvent and the provision of a photosensitive resin or a  
15 photosensitive resin composition capable of being developed with neutral water <sup>only</sup> alone have ~~been long~~ <sup>sought</sup> expected. However, there are available <sup>only</sup> limited number of photosensitive resins capable of being developed with neutral water as will be described hereinafter. Whilst a  
20 photosensitive resin which comprises a water-soluble polymer, such as gelatin, casein or poly(vinyl alcohol), and a dichromate added thereto, has been <sup>practically</sup> ~~used in~~ <sup>in</sup> from the past, ~~the~~ <sup>its</sup> utilization ~~thereof~~ has been restricted or excluded, since it contains heavy metal ions and since  
25 it has poor <sup>storage</sup> ~~preservation~~ stability. Similarly, a photosensitive resin using a water-soluble diazo resin as a photo-crosslinking agent, and containing <sup>a</sup> ~~the~~ water-soluble polymer as <sup>mentioned</sup> ~~shown~~ above has been widely utilized. However, the <sup>utilizable</sup> ~~utilizable~~ range <sup>of utilization</sup> of the resin is limited  
30 because the photosensitivity is lower than <sup>that of a</sup> ~~the~~ dichromate-type photosensitive resin, because the resin is ill-suited for a thick photosensitive layer due to coloring of the exposed area and resulting reduction in light transmittance ~~thereof~~ <sup>as</sup> and because the problem <sup>of</sup> ~~in~~ long-term  
35 ~~preservation~~ <sup>storage</sup> stability ~~still~~ remains unsolved. Further,

there has been proposed a composition <sup>in the form of</sup> containing an emulsion of an ethylenically unsaturated compound and a photopolymerizable initiator in poly(vinyl alcohol), and a photo-crosslinking agent blended <sup>into</sup> the emulsion (Japanese Unexamined Patent Publications No. S49-121852, No. S50-108003, No. S59-107343, etc.). <sup>Such a</sup> The composition, however, is unsatisfactory with respect to the water resisting <sup>ance</sup> property, since no crosslinkages are formed in <sup>the</sup> poly(vinyl alcohol) itself.

10 [0007] Materials containing poly(vinyl alcohol) to which hydrophilic residues, <sup>e.g.</sup> ~~representative of which is~~ styrylpyridinium, are bonded have been proposed as a water-soluble photosensitive polymer <sup>s</sup> that ~~has solved~~ the foregoing problems (Japanese Unexamined Patent

15 Publications No. S55-23163, No. S55-62905, No. 58-25303, etc.). These materials have merits <sup>in that</sup> that the sensitivity thereof is higher than that of the above-described water-developing-type photosensitive resins and the <sup>storage</sup> ~~preservation~~ stability <sup>have use</sup> ~~thereof~~ is excellent and, therefore, ~~are used~~ as

20 pattern forming materials, representative of which is a screen platemaking material. However, since the water-insolubilization of the photosensitive polymer is attained only by <sup>a</sup> photo-dimerization reaction, there <sup>is</sup> ~~occurs~~ no great change in physical properties, <sup>e.g.</sup> ~~representative of which is~~

25 hydrophilicity; <sup>the</sup> although a change in solubility in neutral water before and after the light exposure is significant. As a consequence, when the polymer is used as a printing platemaking material, it has poor resistance to an aqueous ink. <sup>Therefore</sup> ~~In this circumstance,~~ <sup>an</sup> improvement of the physical

30 property of the polymer is <sup>sought</sup> ~~devised~~ by using various additives. For example, compositions blended with an aqueous emulsion are proposed in Japanese Unexamined Patent Publications No. S55-62446, No. S60-10245, No. S61-17141, No. 56-122784, No. S60-10245, etc. However,

35 problems in various physical properties such as water

resistance and mechanical strengths still remain unsolved.  
[0008] Thus, <sup>resist materials have been</sup> ~~there is~~ widely adopted, <sup>wherein</sup> ~~a method in which,~~  
likewise, ~~quinonediazido-type resist material and chemical~~  
proliferation-type resist material, an acidic group such  
5 as a carboxyl group or a phenolic hydroxyl group is  
produced by the catalytic action of an acid generated as a  
result of <sup>a</sup> photochemical reaction, the acidic group being  
utilized for ~~the~~ solubilization <sup>of the resist</sup> in an aqueous alkali  
solution. With this method, a positive-type or negative-  
10 type pattern can be formed by ~~a development treatment~~ with  
an aqueous alkali solution (see C. P. Wong, Polymers for  
Electronic and Photonic Applications, Academic Press, p.67  
(1993)). Because these constituents are insoluble or  
sparingly soluble in water, the composition is prepared ~~as~~  
15 ~~into a~~ solution in an organic solvent. As a consequence,  
there arises a problem <sup>in</sup> that the organic solvent evaporates  
and ~~is scattered~~ <sup>disperses</sup> during the coating <sup>operation for forming</sup> of a film. In a  
photolithographic process ~~in which production is carried~~  
~~out in~~ <sup>on</sup> an extremely large <sup>scale</sup> quantity, it is necessary to  
20 neutralize the developing liquid before discarding.  
Additionally, depending upon the intended use, there  
arises <sup>the</sup> a problem that the physical properties of the  
pattern resist layer <sup>will</sup> deteriorate <sup>due to the presence of</sup> since acidic groups  
having a high polarity ~~are~~ formed in the exposed area. On  
25 the other hand, a method <sup>has</sup> <sup>been</sup> ~~is~~ also proposed in which  
alkaline residues, representative of which is an amino  
group, are formed by photochemical reaction and in which  
development is carried out using acidic water. Since,  
however, a film coating step using an organic solvent must  
30 be included in this method, <sup>addition of</sup> ~~it is unavoidable to carry out~~  
a neutralizing treatment ~~likewise~~ in the alkali  
development. <sup>becomes unavoidably necessary</sup>

[0009] <sup>an</sup> Thus, in photosensitive compositions containing  
~~a photo~~ acid generating agent ~~as its component~~, it is ~~a~~  
35 general practice to dissolve the acid generating agent in

a solvent or other liquid component. As a consequence, when the solvent for the photosensitive composition and the solvent for development are limited to water, it is necessary that the ~~photo~~<sup>acid</sup> generating agent or a  
5 photosensitizer thereof <sup>for</sup> should be soluble in water. Japanese Unexamined Patent Publication No. H09-319080 proposes a water-developable photosensitive composition containing poly(vinyl alcohol), a crosslinking agent and a water-soluble ~~photo~~<sup>acid</sup> generating agent. The  
10 composition has a problem because the ~~kind~~<sup>type</sup> of the water-soluble acid generating agent is restricted and because the acid generated is a carboxylic acid which is low in acidity. On the other hand, Japanese Unexamined Patent Publication No. H10-62990 proposes a photosensitive  
15 composition for screen printing which is developable with water and which is prepared by emulsifying a liquid epoxy resin ~~compound~~<sup>in</sup> into an aqueous solution of poly(vinyl alcohol) containing a cationic photoinitiator to form an oil-in-water type emulsion. In actual<sup>practice</sup>, however, ~~the~~<sup>is added</sup>  
20 ~~composition is added with~~ a diazo resin or dichromate<sup>as</sup> as a water-soluble photo-crosslinking agent or the composition uses poly(vinyl alcohol) into which a photo-crosslinkable stilbazolium group has been introduced. The reason is  
~~considered to be~~ that, because the liquid epoxy resin  
25 containing the cationic photoinitiator is emulsified in the aqueous solution of poly(vinyl alcohol), the reaction of the acid generated by irradiation of a resin film made of the composition with the hydroxyl groups of the poly(vinyl alcohol) which is in a discontinuous phase from  
30 the epoxy resin does not easily occur, though the acid generated can induce the cationic polymerization of the epoxy resin. Thus, the proposed composition has a problem that crosslinking does not sufficiently proceed in the absence of the photo-crosslinking agent.  
35 [0010] ~~The objective problem~~<sup>Thus, an object</sup> of the present invention

is to provide an activation energy ray-sensitive resin composition which is capable of being developed with neutral water, an activation energy ray-sensitive resin film obtainable from the composition, and a pattern forming method using the film.

### SUMMARY OF THE INVENTION

#### ~~Disclosure of the Invention~~

[0011] The present inventors have made an earnest study with a view to solving the above-described problems and, as a result, have accomplished the present invention.

[0012] In accordance with the present invention, there are provided an activation ~~energy ray~~<sup>radiation</sup>-sensitive resin composition which is capable of being developed with neutral water, an activation ~~energy ray~~<sup>radiation</sup>-sensitive resin film which is capable of being developed with neutral water, and a pattern forming method as follows.

[0013] (1) An activation energy ray-sensitive resin composition, characterized in that said composition comprises:  
a dispersion comprising an aqueous solution of a water-soluble resin, and an acid former generating an acid by the action of activation energy rays and being insoluble or sparingly soluble in water, said acid former being dispersed in said aqueous solution in the form of fine powder, and

an acid-reactive insolubilizing agent dissolved or dispersed in said dispersion and insolubilizing said water-soluble resin by the action of said acid

[0014] (1) ~~The~~<sup>of the invention</sup> activation energy ray-sensitive resin composition, characterized in that said composition comprises:

a dispersion comprising an aqueous solution of a water-soluble resin, an acid former <sup>which</sup> generating an acid <sup>es</sup> by ~~the action of activation energy rays~~<sup>ed by radiation</sup> and being insoluble or sparingly soluble in water, and a sensitizer <sup>when</sup>



for sensitizing the acid forming reaction, said acid former and sensitizer being dispersed in said aqueous solution in the form of fine powder, and

an acid-reactive insolubilizing agent dissolved or  
5 dispersed in said dispersion and insolubilizing said water-soluble resin by the action of said acid.

[0015] <sup>The radiation</sup> (3) ~~An activation energy ray-sensitive resin composition as recited in (1) or (2) above, characterized in that a compound having at least one radically~~  
10 ~~polymerizable unsaturated bond, is dissolved or dispersed.~~

[0016] ~~(4) An activation energy ray-sensitive resin composition as recited in any one of (1) through (3) above, characterized in that said acid-reactive insolubilizing agent~~  
15 ~~containing compound, a hydroxymethylated phenol derivative or a resol resin.~~

No. 41 → [0017] ~~(5) An activation energy ray-sensitive resin composition as recited in any one of (1) through (3) above, characterized in that said acid-reactive insolubilizing agent~~  
20 ~~is a compound having at least one epoxy group, oxetane group, vinyloxy group, isopropenyloxy group, or orthoester group, formyl group or acetal group.~~

[0018] ~~(6) An activation energy ray-sensitive resin composition as recited in any one of (1) through (3) above, characterized in that said acid-reactive insolubilizing agent has at least one formyl group.~~


[0019] ~~(7) An activation energy ray-sensitive resin composition as recited in any one of (1) through (3) above, characterized in that said acid-reactive insolubilizing agent has at least one acetal group.~~

[0020] ~~(8) An activation energy ray sensitive resin composition as recited in any one of (1) through (7) above, characterized in that an aqueous resin emulsion, is mixed.~~

[0021] ~~(9) An activation energy ray-sensitive resin composition comprising the activation energy ray sensitive~~  
35

optionally, the radiation-sensitive

- ~~resin composition as recited in any one of (1) through (8) further comprises~~  
~~above, and a water-soluble, photo-insolubilizable resin,~~  
~~[0022] (10) An activation energy ray-sensitive resin composition as recited in any one of (1) through (9) above,~~  
5 ~~characterized in that said water-soluble, photo-~~  
~~insolubilizable resin is a photo-crosslinkable poly(vinyl alcohol) into which a styrylpyridinium group represented by the following general formula (1) has been introduced:~~



- 10 wherein R<sub>1</sub> represents a hydrogen atom, an alkyl group or an aralkyl group, R<sub>2</sub> represents a hydrogen atom or a lower alkyl group, X<sup>-</sup> represents a halogen ion, a phosphate ion, a p-toluenesulfonate ion or a mixture of these anions, m is a number of 0 or 1 and n is an integer of 1 to 6.
- 15 ~~[0023] (11) An activation energy ray-sensitive resin composition as recited in any one of (1) through (9) above,~~  
~~In one preferred embodiment the~~  
~~characterized in that said water-soluble, photo-~~  
~~insolubilizable resin comprises poly(vinyl alcohol),~~  
~~casein or gelatin, and a water-soluble diazo resin or a~~  
20 ~~dichromate.~~  
~~[0024] (12) An activation energy ray-sensitive resin film characterized in that an activation energy ray-sensitive resin composition according to any one of (1) through (11) above is formed into a film. Such a~~  
~~[0025] (13) An activation energy ray-sensitive resin film for screen printing process, characterized in that an activation energy ray-sensitive resin composition according to any one of (1) through (11) above is formed into a film.~~  
25 ~~[0026] (14) A pattern forming method characterized in that an activation energy ray-sensitive resin film~~  
~~wherein the~~

~~according to (12) or (13) above is irradiated with~~  
~~activation energy rays, the resulting film being developed~~  
with water, optionally after having been heat-treated for  
facilitating the acid-catalyzed insolubilization reaction.

5

## DESCRIPTION OF THE PREFERRED EMBODIMENTS


~~Best Mode for Carrying Out the Invention~~

[0027] ~~As~~ the water-soluble resin serving as a  
dispersing agent for finely dispersing the acid former  
and/or sensitizer in the present invention, ~~there~~ may be  
10 ~~used~~ any naturally occurring polymer, semi-synthetic  
polymer <sup>or</sup> synthetic polymer (refer to "Development  
Techniques of Water-Soluble Polymers", CMC (1999)). ~~As~~  
<sup>suitable</sup> the naturally occurring polymers <sup>include</sup> ~~there may be mentioned~~  
chitin, chitosan, casein, collagen, albumen, starch, <sup>suitable</sup>  
15 carrageenan, xanthan gum, dextran, pullulan, etc. ~~As the~~  
semi-synthetic polymers <sup>include</sup> ~~there may be mentioned~~ dialdehyde  
starch, partial hydrolysate of starch, hydroxyethyl starch,  
cyclodextrin, dextrin, carboxymethyl cellulose, methyl  
cellulose, hydroxyethyl cellulose, hydroxypropyl cellulose,  
20 etc. <sup>suitable</sup> ~~As the~~ synthetic polymers <sup>include</sup> ~~there may be mentioned~~  
poly(vinyl alcohol), partially saponified poly(vinyl  
alcohol), poly(vinyl alcohol) acetalized such that the  
water solubility is not lost, poly(vinylpyrrolidone) and  
copolymers thereof, polyacrylamide and copolymers thereof,  
25 N-isopropylacrylamide and copolymers thereof, acrylamide  
and copolymers thereof, N,N-dimethylacrylamide and  
copolymers thereof, poly(N-acetylvinylamine), polyethylene  
glycol, etc.

[0028] Polymers having basic residues may also be used  
30 for the purpose of the present invention, since ~~the~~  
reduction of <sup>the</sup> acidity ~~of the acid~~ generated ~~from~~ <sup>by</sup> the acid  
former can be prevented by adjusting the pH of the aqueous  
solution <sup>to</sup> ~~at~~ about 7. However, it is ~~more~~ preferred that  
the water-soluble polymer chains <sup>be</sup> ~~are~~ free of amino groups  
35 which are basic residues or that the amount of amino

groups be as small as possible. It is also preferred that the water-soluble polymers contain functional groups capable of reacting with the acid-reactive insolubilizing agent, such as hydroxyl groups. In this regard, starch, dialdehyde starch, methyl cellulose, hydroxyethyl cellulose, hydroxypropyl cellulose, poly(vinyl alcohol), polyacrylamide, hydroxyethyl acrylate copolymers, hydroxyethyl methacrylate copolymers, water-soluble N-methylolated nylon, etc. are suitably used. Since these water-soluble polymers also ~~serve to~~ function as a dispersant for the solid photo-acid former, cationic residues may be introduced thereto.

[0029] These water-soluble resin<sup>s</sup> may be added as a binder resin to a fine dispersion of the acid former and/or sensitizer. Further, these water-soluble binder resins may be used together with a diazo resin or a dichromate as a photo-crosslinking agent. Furthermore, a photo-crosslinkable poly(vinyl alcohol), disclosed in Japanese Unexamined Patent Publications No. S55-23163, No. 55-62905, etc. and containing a styrylpyridinium group represented by the general formula (1) shown below, may be suitably used as the binder resin:



[0030] In the above formula, R<sub>1</sub> represents a hydrogen atom, an alkyl group or an aralkyl group, R<sub>2</sub> represents a hydrogen atom or a lower alkyl group, X<sup>-</sup> represents a halogen ion, a phosphate ion, a p-toluenesulfonate ion or a mixture of these anions, m is ~~a number of~~ 0 or 1 and n is an integer of 1 to 6.

[0031] The alkyl group R<sub>1</sub> has 1 to 6 carbon atoms, preferably 2 to 4 carbon atoms.

No. 4  
[0032] The aralkyl group  $R_1$  has 7 to 13 carbon atoms, preferably 7 to 10 carbon atoms. The aralkyl group ~~is~~ <sup>may be</sup> derived from various aromatic compounds (benzene compounds, naphthalene compounds, anthracene compounds, etc.) having alkyl groups.

[0033] The lower alkyl group  $R_2$  has 1 to 4 carbon atoms, preferably 1 to 2 carbon atoms.

[0034] ~~As the acid former~~ <sup>which</sup> ~~generating~~ <sup>es</sup> an acid by the action of activation ~~energy rays~~ <sup>radiation</sup> according to the present invention, ~~there~~ <sup>at</sup> may be ~~used~~ <sup>used</sup> compounds utilized in chemical amplification-type photoresists or in cationic photopolymerization (refer to "Organic Materials for Imaging", edited by Organic Electronics Material Study Group, Bunshin Shuppan (1993)). ~~As the acid former~~ <sup>suitable</sup> ~~used~~ <sup>for</sup> in the present invention, ~~there may be mentioned a~~ <sup>include</sup> cationic onium compound, ~~a~~ halogen-containing compound which generates a hydrogen halide, and ~~a~~ sulfonated compound which generates sulfonic acid. These compounds are insoluble or sparingly soluble in water. Examples of such suitable compounds are ~~shown~~ <sup>given</sup> below.

[0035] ~~As the ionic acid former~~ <sup>suitable</sup> ~~there may be mentioned~~ <sup>include</sup> salts of onium cations, such as diazonium, ammonium, iodonium, sulfonium, phosphonium or ferrocenium, with  $Cl^-$ ,  $Br^-$ ,  $I^-$ ,  $ZnCl_3^-$ ,  $HSO_3^-$ ,  $BF_4^-$ ,  $PF_6^-$ ,  $AsF_6^-$ ,  $SbF_6^-$ ,  $CH_3SO_3^-$ ,  $CF_3SO_3^-$ , perfluorobutanesulfonate, perfluorooctanesulfonate, camphorsulfonate, benzenesulfonate, p-toluenesulfonate, 9,10-dimethoxyanthracene-2-sulfonate, cyclohexylamino sulfonate,  $(C_6F_5)_4B^-$ ,  $(C_4H_9)_4B^-$ , etc. <sup>compounds</sup>

[0036] Specific examples of the onium cation <sup>include</sup> phenyldiazonium, p-methoxy diazonium,  $\alpha$ -naphthyldiazonium, biphenyldiazonium, diphenylamine-4-diazonium, 3-methoxydiphenylamine-4-diazonium, 2,5-diethoxy-4-methoxybenzoylamidophenyldiazonium, 2,5-dipropoxy-4-(4-tolyl)thiophenyldiazonium, 4-methoxydiphenylamine-4-diazonium, condensate of 4-diazodiphenylamine and

formaldehyde, 1-methoxyquinolinium, 1-ethoxyisoquinolinium, 1-phenacylpyridinium, 1-benzyl-4-benzoylpyridinium, 1-benzylquinolinium, N-substituted benzothiazolium (refer to Japanese Unexamined Patent Publication No. H05-140143),  
 5 etc. *Further examples include*  
 No. 77-0 ~~[0037]~~ Further, there may be mentioned benzyltriphenyl sulfonium, p-methoxyphenyldiphenyl sulfonium, bis(p-methoxyphenyl)phenyl sulfonium, tris(p-methoxyphenyl) sulfonium, p-phenylthiophenyldiphenyl sulfonium,  
 10 benzyltetramethylene sulfonium, phenacyltetramethylene sulfonium, phenacyldimethyl sulfonium, p-methoxyphenyldiethyl sulfonium, naphthyldialkyl sulfonium (refer to Japanese Unexamined Patent Publications No. H09-118663 and No. H05-140209), (2-naphthylcarbonylmethyl)-  
 15 tetramethylene sulfonium, (p-hydroxyphenyl)dimethyl sulfonium, (4-hydroxynaphthyl)dimethyl sulfonium, (4,7-dihydroxynaphthyl)-1-dimethyl sulfonium, (4,8-dihydroxynaphthyl)-1-dimethyl sulfonium, diphenyl iodonium, phenyl(4-methoxyphenyl) iodonium, phenyl{4-(tert-butyl)phenyl}iodonium, 4-bis{4-(tert-butyl)phenyl} iodonium, bis(4-dodecylphenyl) iodonium, (4-methoxyphenyl)-4-octyloxyphenyl) iodonium, phenacyltriphenyl phosphonium, cyanomethyltriphenyl phosphonium, etc.  
 20 *suitable*  
 25 [0038] Examples of the acid former generating a halogenated hydroacid include 1-methyl-3,5-bis(trichloromethyl)-s-triazine, 1-phenyl-3, 5-bis(trichloromethyl)-s-triazine, 1-(4-chlorophenyl)-3, 5-bis(trichloromethyl)-s-triazine, 1-(4-methoxyphenyl)-3, 5-bis(trichloromethyl)-s-triazine, 1-(4-butoxyphenyl)-3, 5-bis(trichloromethyl)-s-triazine, 1-(3, 4-methylenedioxyphenyl)-3,5-bis(trichloromethyl)-s-triazine, 1-(3,4-dimethoxyphenyl)-3, 5-bis(trichloromethyl)-s-triazine, 1-(4-methoxynaphthyl-1)-3, 5-bis(trichloromethyl)-s-triazine, 1-(2-(4-

methoxyphenyl)ethenyl)-3,5-bis(trichloromethyl)-s-triazine,  
 1-{2-(2-methoxyphenyl)ethenyl}-3,5-bis(trichloromethyl)-s-  
 triazine, 1-{2-(3,4-dimethoxyphenyl)ethenyl}-3,5-  
 bis(trichloromethyl)-s-triazine, 1-{2-(3-chloro-4-  
 5 methoxyphenyl)ethenyl}-3,5-bis(trichloromethyl)-s-triazine,  
 1-(biphenyl-1)-3,5-bis(trichloromethyl)-s-triazine, 1-(4-  
 hydroxybiphenyl-1)-3,5-bis(trichloromethyl)-s-triazine, 1-  
 (4-methoxybiphenyl-1)-3,5-bis(trichloromethyl)-s-triazine,  
 1-(4-methylbiphenyl-1)-3,5-bis(trichloromethyl)-s-triazine,  
 10 1,3,5-tris(trichloromethyl)-s-triazine, 1,3-dichloro-4-  
 trichloromethylbenzene, 1,1,1-trichloro-{2,2,84-  
 chlorophenyl}ethane, phenyltribromomethyl sulfone, 1-keto-  
 4-methyl-4-trichloromethyl-2,5-dichlorohexadiene, 2-  
 tribromoquinoline and 1-keto-2,3-benzo-4,4,5,6-  
 15 tetrachlorohexadiene.  
 [0039] <sup>501 tab</sup> <sup>which e</sup> As the acid former generating sulfonic acid,  
~~include~~ ~~there may be mentioned~~ 2-nitrobenzyl-p-toluene sulfonate,  
 2,6-dinitrobenzyl-p-toluene sulfonate, 1-(p-  
 toluenesulfonyloxyimino)-1-phenylethane nitrile, 1-(p-  
 20 toluenesulfonyloxyimino)-1-phenylethanenitrile, benzoin-p-  
 toluenesulfonate, 2-p-toluenesulfonyloxy-2-benzoylpropane,  
 p-nitrobenzyl-9,10-dimethoxyanthracene-2-sulfonate, N-  
 trifluoromethanesulfonyloxydiphenylmaleimide, N-p-  
 toluenesulfonyloxysuccinimide, N-  
 25 camphorsulfonyloxysuccinimide, N-  
 trifluoromethanesulfonyloxysuccinimide, N-  
 perfluorobutanesulfonyloxysuccinimide, N-p-  
 toluenesulfonyloxyphthalimide, N-  
 camphorsulfonyloxyphthalimide, N-  
 30 trifluoromethanesulfonyloxyphthalimide, N-  
 perfluorobutanesulfonyloxyphthalimide, N-p-  
 toluenesulfonyloxy-1,8-naphthalenecarboxyimide, N-  
 camphorsulfonyloxy-1,8-naphthalenecarboxyimide, N-  
 trifluoromethanesulfonyloxy-1,8-naphthalenecarboxyimide,  
 35 N-perfluorobutanesulfonyloxy-1,8-naphthalenecarboxyimide,

1,2,3-tris(p-toluenesulfonyloxy)benzene,  
bis(phenylsulfone), bis(phenylsulfonyl)methane, etc.

[0040] The above-described acid formers which are  
insoluble or sparingly soluble in water are ~~used by being~~  
5 finely dispersed in the aqueous solution of the water-  
soluble resin. Therefore, the acid generated by  
activation ~~energy rays~~ <sup>radiation</sup> can easily diffuse in the water-  
soluble resin. As a consequence, the acid-catalyzed  
reaction of the acid-reactive insolubilizing agent and the  
10 water-soluble resin is facilitated so that the  
insolubilization of the resin can efficiently proceed.  
[0041] In the present invention, ~~while~~ <sup>mentioned</sup> the acid  
formers ~~exemplified~~ <sup>mentioned</sup> above can generate, by themselves, the  
corresponding acid by the action of activation ~~energy rays~~ <sup>radiation</sup>,  
15 the acid can be also generated when ~~they are~~ <sup>they are</sup> irradiated, in the  
presence of a spectrum sensitizer, with light which can be  
absorbed by the sensitizer. The spectrum sensitizer used  
for the purpose of the present invention is desirably  
insoluble or sparingly soluble in water. Thus, the  
20 desired objects may be achieved when the acid former is  
dispersed together with the sensitizer in the form of fine  
powder. It ~~is~~ <sup>was</sup> unexpected that the sensitized acid forming  
reaction efficiently ~~occurs to cause the~~ <sup>gave</sup> insolubilization  
even when not only the acid former but also the sensitizer  
25 is in the form of dispersed solids.

[0042] The sensitizer used in the present invention is  
preferably an electron donating compound in view of the  
fact that the above-exemplified acid formers function as  
~~an~~ <sup>s</sup> electron donor, as described in Japanese Unexamined  
30 Patent Publications No. S54-151024, No. S58-40302, No.  
S60-76740, No. S60-78443, No. S60-88005, No. S60-112802,  
No. S61-97650, No. S61-180359, No. S62-161820 and No. S63-  
243102. ~~As the sensitizer having such a property and~~ <sup>Such</sup>  
~~suitable for the present invention, there may be mentioned,~~ <sup>include,</sup>  
35 but not limited ~~thereto,~~ <sup>thereby</sup> an aromatic polycyclic compound,



5 a porphyrin compound, a phthalocyanine compound, a polymethine dye compound, a merocyanine compound, a coumarin compound, a thiopyrylium compound, a pyrylium compound, a p-dialkylaminostyryl compound, a thioxanthene compound etc. Most of these compounds are disclosed in "Dye Handbook" (Kodansha) edited by Ookawara, Hirashima, Matsuoka and Kitao; "Handbook of Coloring Material Engineering" (Asakura Publishing (1989)), edited by the Japan Society of Coloring Material; and "Dye Catalogue" of Hayashibara Biochemical Laboratories Photosensitive Dye Lab.

10 *Sub Table*  
 [0043] ~~As the aromatic polycyclic compound, there may be mentioned~~ those which have a basic skeleton of a hydrocarbon such as naphthalene, phenanthrene, pyrene, anthracene, tetracene, chrysene, pentacene, picene, coronene, hexacene or ovalene. Also, aromatic five-membered ring heteropolycyclic compounds containing an oxygen atom, a nitrogen atom or a sulfur atom ~~as their constituent atoms~~, such as benzofuran, dibenzofuran, indole, carbazole, benzothiophene and dibenzothiophene, may be ~~mentioned~~ *used*. Usable aromatic six-membered ring heteropolycyclic compounds have a basic skeleton of, for example,  $\alpha$ -benzopyrone,  $\beta$ -benzopyrone,  $\alpha$ -thiabenzopyrone,  $\beta$ -thiabenzopyrone, flavone, xanthone, thioxanthone, phenoxazine or phenothiazine. These basic skeletons may have at least one electron donating group, ~~as a substituent~~, such as an alkyl group, a hydroxyl group, an alkoxy group or an alkylthio group. Examples of the sensitizer *in the form* of substituted aromatic polycyclic compounds

20 include 1-methoxynaphthalene, 1,4-dimethylnaphthalene, 1,8-dimethylnaphthalene, 9,10-dimethylphenanthrene, 9-methylantracene, 9,10-dimethylantracene, 9,10-diphenylantracene, 9,10-bis(phenylethynyl)anthracene, 1,8-dimethyl-9,10-bis(phenylethynyl)anthracene, 9,10-dimethoxyanthracene, 9,10-diethoxyanthracene, 9,10-

30  
 35

- dipropoxyanthracene, 9,10-dibutoxyanthracene, <sup>and</sup> 1-methylpyrene. <sup>suitable</sup> ~~As the~~ substituted polycyclic heterocyclic compounds <sup>include</sup> ~~there may be mentioned~~ N-methylcarbazole, N-ethylcarbazole, thioxanthone, isopropylthioxanthone, etc.
- 5 [0044] The porphyrin compound may be a compound having a basic skeleton of, for example, tetraphenylporphine, octaethylporphine, mesoporphyrin, protoporphyrin, hematoporphyrin, chlorin, tetrabenzoporphine, phenyl-substituted tetrabenzoporphine, a magnesium complex, <sup>or</sup> a zinc complex thereof. Also, <sup>suitable</sup> ~~there may be mentioned~~ chlorophyll.
- 10 [0045] The phthalocyanine compound may be a naphthocyanine compound and may have at least one substituent, such as an alkyl group, an alkoxy group, an alkylthio group, an aryl group <sup>or</sup> and a halogen group, introduced into its basic skeleton. Further, as a central metal, magnesium, zinc, cadmium or aluminum is particularly preferred.
- 15 [0046] As the polymethine dye compound, a cyanine-series or merocyanine-series compound having <sup>ic structure</sup> ~~such a structure in which~~ a heterocycle containing a nitrogen atom, an oxygen atom, a sulfur atom, etc. <sup>based to</sup> ~~is connected by~~ polymethine can be used. <sup>such</sup> ~~for example, compounds disclosed in "Dye Handbook" edited by Makoto OOKAWARA, Teijiro KITAO,~~
- 20 Tsuneaki HIRAOKA and Ken MATSUOKA, (Kodansha Scientific (1986)), pages 382-417, ~~may be mentioned.~~ Specific examples of the dye compounds include <sup>compounds</sup> ~~a cyanine-series which~~ comprises <sup>in</sup> a quinoline ring, <sup>in</sup> ~~an indiocyanine-series which~~ comprises <sup>in</sup> an indole ring, <sup>in</sup> ~~a thiocyanine-series which~~ comprises <sup>in</sup> a benzothiazole ring, and <sup>in</sup> ~~a polymethine-series which~~ comprises <sup>in</sup> an iminocyclohexadiene ring, and <sup>compounds</sup> ~~additionally, a benzoxazole-series, a pyrylium-series, a thiapyrylium-series, a squarylium-series, a croconium-series.~~ <sup>compounds</sup> ~~may be used~~ <sup>chosen from</sup>
- 30 [0047] ~~As~~ <sup>the</sup> coumarin compound, ~~there~~ <sup>may be mentioned</sup>

*among the*

- monocoumarin compounds described in "Dye Handbook" edited by Makoto OOKAWARA, Teijiro KITAO, Tsuneaki HIRAOKA and Ken MATSUOKA, (Kodansha Scientific (1986)), pages 432-438 and, additionally, 3-(2-benzothiazolyl)-7-
- 5 (diethylamino)coumarin, 3-(2-benzothiazolyl)-7-  
(dibutylamino)coumarin, 3-(2-benzothiazolyl)-7-  
(dioctylamino)coumarin, 3-(2-benzo imidazolyl)-7-  
(diethylamino)coumarin, 10-(2-benzothiazolyl)-2,3,6,7-tetrahydro-1,1,7,7-tetramethyl-1H,5H,11H-
- 10 [1]benzopyrano[6,7,8-ij]quinolizine-11-one, 3,3-carbonylbis(7-diethylaminocoumarin), 3,3-carbonylbis(7-dibutylaminocoumarin), etc.
- [0048] *splitable* As the p-dialkylaminostyryl compound *include* ~~there may~~  
~~be mentioned~~ 4-diethylaminobenzylideneacetophenone,
- 15 4-diethylaminobenzylidene(p-methoxy)acetophenone,  
4-diethylaminobenzylidenemalonitrile,  
4-dimethylaminobenzylideneacetoacetic ethyl ester,  
4-dimethylaminobenzylidenemalonic acid diethyl ester,  
4-dimethylaminobenzylidene- $\alpha$ -cyanoacetophenone,
- 20 2,6-bis(4-dimethylaminobenzylidene)cyclohexanone,  
4-dimethylaminocinnamylideneacetophenone,  
4-dimethylaminocinnamylidenemalonitrile,  
4-dimethylaminocinnamylidenecyanoacetic acid ethyl ester,  
4-dimethylaminocinnamylidenemalonic acid diethyl ester,
- 25 4-dimethylaminocinnamylidene- $\alpha$ -cyanoacetophenone,  
4-dimethylaminocinnamylidenebis(4-dimethylaminobenzylidene)cyclohexanone, etc.
- [0049] The absorption wavelengths of these ~~spectrum~~  
sensitizers encompass a wide range from ~~those of~~  
30 ultraviolet ~~rays~~ to ~~those of~~ infrared ~~rays~~. Thus, they  
can be used singly or as a mixture of two or more thereof  
so that light of a wide range of wavelengths can be  
efficiently absorbed for the generation of the acid.  
The term "acid-reactive insolubilizing agent" as used  
35 herein is intended to refer to a compound which causes

dehydrative condensation reactions, addition reactions, cationic polymerization reactions, etc. by the catalytic action of <sup>the</sup> an acid generated by the ~~action of~~ activation ~~energy rays~~ <sup>radiation</sup>, so that the water-soluble resin contained in

5 the composition is insolubilized through crosslinking, polymerization, etc. In particular, it is preferred that the insolubilizing agent be acid-catalytically bonded to the main chain or side chain cites of the water-soluble resin. The insolubilizing agent may be soluble, insoluble

10 or sparingly soluble in water. An insolubilizing agent which is insoluble or sparingly soluble in water may be used in the form of a dispersion. The insolubilizing agents ~~which will be exemplified~~ <sup>mentioned</sup> below may be used alone or as a mixture of two or more thereof.

15 [0050] ~~As an~~ <sup>I</sup> insolubilizing agent <sup>5</sup> which undergoes <sup>11</sup> dehydrative condensation with alcoholic hydroxyl groups of poly(vinyl alcohol), cellulose derivatives, polysaccharides such as starch, N-methylolated nylon, etc. as the water-soluble resin, ~~there may be mentioned~~ <sup>include</sup> N-

20 hydroxymethylacrylamide, N-hydroxymethylated urea, N-hydroxymethylated malonamide, N-hydroxymethylated phthalamide, hexahydroxymethylated melamine, p-hydroxymethylphenol, o-hydroxymethylphenol, 2,6-bis(hydroxymethyl)-p-cresol, resol resin, etc.

25 Derivatives of these compounds in which the hydroxymethyl group is replaced by an alkoxymethyl group having 1-6 carbon atoms may also be used.

[0051] <sup>suitable</sup> ~~As an~~ <sup>8</sup> insolubilizing agent <sup>5</sup> which undergoes <sup>11</sup> addition reaction with alcoholic hydroxyl groups of

30 poly(vinyl alcohol), cellulose derivatives, polysaccharides such as starch, and derivatives thereof as the water-soluble resin, <sup>include</sup> ~~a~~ <sup>5</sup> compound having at least one epoxy group or oxetane group, ~~may be suitably used~~. Such a compound ~~causes also~~ cationic polymerization and is

35 particularly preferred. <sup>suitable</sup> ~~As the~~ insolubilizing agent <sup>5</sup>

having two or more glycidyl-type epoxy groups, <sup>include</sup> ~~there may~~  
~~be mentioned~~ EX-611, EX-612, EX-614, and EX-614B EX-614,  
 EX-622, EX-512, EX-521, EX-411, EX-421, EX-313, EX-314,  
 EX-321, EX-201, EX-211, EX-212, EX-252, EX-810, EX-811,  
 5 EX-850, EX-851, EX-821, EX-830, EX-832, EX-841, EX-861,  
 EX-911, EX-941, EX-920, EX-721, EX-221, EM-150, EM-101 and  
 EM-103, which are DENAKOL-series products described in a  
 catalog of Nagase Chemtex Co., Ltd.; YD-115, YD-115G, YD-  
 115CA, YD-118T and YD-127, which are described in a  
 10 catalog of Toto Kasei Co., Ltd.; and 40E, 100E, 200E, 400E,  
 70P, 200P, 400P, 1500NP, 1600, 80MF, 100MF, 4000, 3002 and  
 1500, which are EPOLITE-series products described in a  
 catalog of Kyoeisha chemical Co., Ltd. <sup>Suitable</sup> ~~As an~~ alicyclic  
 epoxy compound, <sup>include</sup> ~~there may be mentioned~~ CELOXIDE 2021,  
 15 CELOXIDE 2080, CELOXIDE 3000, EPOLEAD GT300, EPOLEAD GT400,  
 EPOLEAD D-100ET, EPOLEAD D-100OT, EPOLEAD D-100DT, EPOLEAD  
 D-100ST, EPOLEAD D-200HD, EPOLEAD D-200E, EPOLEAD D-204P,  
 EPOLEAD D-210P, EPOLEAD D-210P, EPOLEAD PB3600, EPOLEAD  
 PB4700, etc. described in a catalog of Daicel Chemical  
 20 Industries, Ltd.  
 [0052] <sup>Suitable</sup> ~~As a~~ monofunctional epoxy compound, <sup>include</sup> ~~there may~~  
~~be mentioned~~ EX-111, EX-121, EX-141, EX-145, EX-146, EX-  
 171, EX-192, EX-111 and EX-147, which are DENAKOL-series  
 products described in a catalog of Nagase Chemtex Co.,  
 25 Ltd.; and M-1230, EHDG-L and 100MF which are EPOLITE-  
 series products described in a catalog of Kyoeisha  
 chemical Co., Ltd. By using these substances as a  
 reactive diluent, a highly viscous or solid epoxy resin  
 can be used, ~~for~~ <sup>for</sup> example, BPF-type epoxy resins, BPA-type  
 30 epoxy resins, BPF-type epoxy resins, novolak-type epoxy  
 resins, brominated-type epoxy resins and flexible-type  
 resins, which are described in a catalog of Tohto Kasei  
 Co., Ltd.; EPIKOTE basic solid-type and EPIKOTE bis-F  
 solid-type described in a catalog of Yuka Shell Epoxy  
 35 Kabushiki Kaisha; and EHPE alicyclic-type solid epoxy

resins described in a catalog of Daicel Chemical Industries, Ltd., ~~can be used.~~

- 5 [0053] As an oxetane compound, there may be used compounds described in J. V. Crivello and H. Sasaki, J. M. S. Pure Appl. Chem., A30 (2&3), 189 (1993) or J. H. Sasaki and V. Crivello, J. M. S. Pure Appl. Chem., A30 (2&3), 915 (1993). <sup>suitable</sup> ~~For example,~~ <sup>include</sup> OXT-101, OXT-121, OXT-211, OXT-221, OXT-212, OXT-611, etc. of Toa Gosei, Inc., ~~can be mentioned.~~ These oxetane compounds may be used as a mixture with the
- 10 above-mentioned epoxy compound.
- [0054] <sup>suitable</sup> ~~As an~~ insolubilizing agent <sup>for</sup> ~~which causes~~ cationic polymerization, <sup>include</sup> ~~there may be mentioned,~~ in addition to the above epoxy groups and oxetane groups, <sup>compounds</sup> monomers having a vinyl ether group, a propenyl ether group or a cyclic
- 15 ortho-ester group. <sup>suitable</sup> ~~As~~ vinyl ether, <sup>include</sup> ~~there may be mentioned~~ butane diol divinyl ether, hexane diol divinyl ether, cyclohexane diol divinyl ether, diethylene glycol mono-vinyl ether, diethylene glycol divinyl ether, hydroxybutyl vinyl ether, hydroxyethyl vinyl ether, octadecyl vinyl
- 20 ether, butanediol monovinyl ether.
- [0055] In the composition according to the present invention, a compound having at least one, more preferably at least two, formyl groups or acetal groups can be used as an acid reactive insolubilizing agent, when using
- 25 polyvinyl alcohol as the water-soluble resin. In this case, acetalization takes place on the poly(vinyl alcohol) chain with <sup>The</sup> ~~an~~ acid generated serving as a catalyst, <sup>so resulting</sup> ~~so~~ <sup>in a insoluble product.</sup> ~~that the water solubility thereof is lost.~~ Examples of <sup>the</sup> ~~the~~ compound <sup>5</sup> having a formyl group include salicylaldehyde,
- 30 m-hydroxybenzaldehyde, p-hydroxybenzaldehyde, terephthalaldehyde, terephthalaldehyde bisethyl acetal, terephthalaldehyde bisethylene acetal, terephthalaldehyde trimethylene acetal, glutaraldehyde bisdiethyl acetal and glutaraldehyde bisethylene acetal.
- 35 [0056] A compound having at least one light-<sup>sensitive</sup> ~~active~~

ethylenically unsaturated bond may be dissolved or dispersed in the photosensitive composition of the present invention. By <sup>addition of</sup> ~~containing~~ such a compound, not only <sup>an</sup> ~~an~~ acid ~~is~~ generated by the decomposition of photo-acid former but also <sup>free</sup> radical ~~species~~ are generated together, so that the composition is imparted with an ability to initiate radical polymerization. The light-<sup>sensitive</sup> ~~active~~ ethylenically unsaturated compound is a compound having at least one radical ~~polymerizable~~ unsaturated bond such as an acryloyl group, a methacryloyl group or an allyl group. The ethylenically unsaturated compound <sup>may be</sup> ~~involves~~ a prepolymer or an oligomer having a molecular weight of 10,000 or less.

[0057] <sup>suitable</sup> ~~As the unsaturated compound, there may be~~ <sup>include</sup> ~~mentioned~~ pentaerythritol (meth)acrylate, pentaerythritol tetra (meth)acrylate, trimethylolpropane tri(meth)acrylate, triallyl isocyanurate, lauryl (meth)acrylate, methoxyethylene glycol (meth)acrylate, 2-ethylhexyl (meth)acrylate, benzyl (meth)acrylate, hexyl diglycol (meth)acrylate, ethylene glycol di(meth)acrylate, diethylene glycol di(meth)acrylate, trimethylene ethylene glycol di(meth)acrylate, tetramethylene glycol di(meth)acrylate, pentamethylene glycol di(meth)acrylate, hexamethylene glycol di(meth)acrylate, ethylene glycol diglycidyl ether (meth)acrylate, phenyl glycidyl ether (meth)acrylate, trimethylolpropane polyglycidyl ether (meth)acrylate, terephthalic acid diglycidyl ether (meth)acrylate, a reaction product of tolylene diisocyanate and 2-hydroxypropyl (meth)acrylate, a reaction product of phenyl isocyanurate and 2-hydroxyethyl (meth)acrylate and an unsaturated polyester with a molecular weight of 10000 or less and having an ethylenically unsaturated bond such as a maleic acid ester of glycol.

[0058] <sup>sensitive</sup> ~~active~~ These light-~~active~~ unsaturated compounds may be

used singly or in combination of two or more and are used in an amount of 0.5 to 5 parts, preferably 0.1 to 3 parts, per 1 part of the water-soluble resin.

5 [0059] These radically polymerizable compounds generate not only acids but also <sup>free</sup> radical species when irradiated with light in the presence of a photo-acid former, alone or in combination with a sensitizer. Therefore, polymerization takes place to cause solubilization. Additionally, a known radical photoinitiator may be  
10 cojointly used to facilitate the photo-radical reaction.

[0060] Next, a method for dispersing the above-described constituents in an aqueous solution of a water-soluble resin so as to obtain the composition of the present invention will be described.

15 [0061] The acid former, <sup>optionally a</sup> and sensitizer ~~which is~~ used, if necessary, by mixing therewith, are sparingly soluble or insoluble in water and are dispersed in an aqueous solution of a water-soluble resin after having been <sup>a</sup> ~~previously~~ finely ground and further pulverized into fine  
20 powder. Alternately, these substances are pulverized in an aqueous solution of a water-soluble resin into <sup>a</sup> fine powder to obtain a suspension in which they are finely dispersed in a solid state. Since the composition of the present invention is used as a water suspension ~~liquid~~, it  
25 is preferred that the acid former and/or sensitizer be finely dispersed in water. Therefore, as a dispersant, the water-soluble resin is suitably used, though a surfactant, etc. <sup>also</sup> may be used ~~together~~.

[0062] Thus, the present invention is characterized in  
30 that ~~the~~ photo-acid former ~~in~~ a solid state is dispersed in water in the form of fine powder. To this end, known ~~fine~~ pulverization methods, ~~fine~~ dispersion methods and apparatuses therefor used for the manufacture of coating materials, pigments, inks, paints, various coatings,  
35 electronic materials, magnetic materials, pharmaceuticals,



agricultural chemicals, cosmetics, food, etc. may be utilized.

- No. 57 <sup>Such</sup> ~~[0063]~~ These methods and apparatuses are disclosed in, for example, Taiichi TSURITANI and Masumi OISHI,
- 5 "Industrial Dispersing Technique", Nikkan Kogyo Shimbun Ltd. (1985); Noboru MORIYAMA, "Chemistry of Dispersion and Aggregation", Sangyo Tosho Publishing (1995), p. 150-154; "Fine Particle Control" edited by Society of Chemical Engineers, Japan, Maki-Shoten Publishing (1996), p. 1-14;
- 10 "Coating", edited by Processing Technique Study Group, Processing Technique Study Group (2002), p. 84-139. Namely, devices such as a colloid mill, a ball mill, a sand mill, a bead mill, three roll mill and, additionally, a kneader, an extruder and a high speed disperser may be used singly
- 15 or in combination. In dry type fine pulverizing of the acid former and/or sensitizer, the pulverized fine powder <sup>is</sup> ~~are~~ dispersed in an aqueous solution of a water soluble resin. In this case, the water soluble resin itself serves as a dispersant. If desired, a low molecular
- 20 weight or high molecular weight surfactant may be also added as a dispersant. In the case of wet pulverizing, since the pulverization and fine-dispersion are carried out in an aqueous solution of a water-soluble resin, a photosensitive composition can (be easily) prepared from the
- 25 suspension itself. In this case, too, a surfactant can be added in order to efficiently perform the dispersion.
- [0064] The following methods may be employed for the dry-type or wet-type pulverization of the photo-acid former in the presence of the spectral sensitizer:
- 30 [0065] In <sup>a</sup> ~~the~~ first method, solids of the photo-acid former and sensitizer are pulverized together into fine powder in an aqueous solution of a water-soluble resin and dispersed therein. Namely, the photo-acid former and sensitizer in the form of a mixture are subjected to ~~a~~ dry
- 35 or wet fine pulverization ~~treatment~~.

[0066] In <sup>a</sup>the second method, a mixture of the acid ~~proliferation agent~~ <sup>former</sup> and sensitizer are dissolved in an organic solvent. Thereafter, while removing the solvent from the solution or after the solvent has been removed therefrom, the mixture is finely dispersed in an aqueous solution of a water-soluble resin.

[0067] In <sup>the</sup> third method, the acid ~~proliferation agent~~ <sup>former</sup> and ~~sensitizer~~ <sup>the</sup> in the solid state are separately ~~and~~ finely dispersed in aqueous solutions of a water-soluble resin. Then, the resulting dispersions are mixed together.

[0068] In a further method for finely dispersing the acid former and/or sensitizer, a solution of them dissolved in an organic solvent is added dropwise <sup>to</sup> in an aqueous solution of a water-soluble resin in accordance with the method disclosed in Japanese Unexamined Patent Publication No. H06-79168 or No. 2001-262137.

[0069] ~~while~~ <sup>the</sup> present inventors expected that, when a ~~photo-acid as a solid~~ is finely dispersed and the dispersion is irradiated ~~with activation energy rays~~, an acid <sup>could be</sup> is generated. However, <sup>they</sup> it is unexpected <sup>to</sup> that ~~the~~ <sup>photo-sensitive</sup> sensitized acid-generation reaction occurs even when both the photo-acid former and the sensitizer are in the form of solids. That is, it ~~is said~~ <sup>had been accepted</sup> that in order for an electron transfer reaction or an energy transfer, which is a sensitization reaction, to take place, it is necessary that the intermolecular distance between a molecule which gives electron or excitation energy (the molecule ~~will be~~ referred to as "donor molecule") and a molecule which receives the electron or excitation energy (the molecule ~~will be~~ referred to as "acceptor molecule") should be <sup>an</sup> ~~up~~ <sup>no</sup> more ~~than~~ <sup>more than</sup> to about 10 angstroms. For this reason, it has been the general practice that the donor molecule and the acceptor molecule are combined into the same molecule, or are dissolved to ~~have~~ <sup>have</sup> a molecule <sup>or</sup> concentration higher than a predetermined level. It <sup>was</sup> ~~is~~ therefore surprising that ~~the~~

radiation sensitized at a high  
sensitization reaction occurs and, hence, the  
sensitization rate of high sensitivity is obtainable, even  
though the photo-acid former and the sensitizer are  
present in the composition of the present invention, <sup>i.e. even though</sup>  
5 dispersed state as solids because they are sparingly  
soluble or insoluble in water. It is inferred that the  
acid former and the sensitizer might form an eutectic  
during the course of mixing and finely dispersing them, or  
might form a solid solution with the acid-reactive  
10 insolubilizing agent and water-soluble resin during the  
course of a film forming process.

[0070] Although the particle size of the acid former  
and/or sensitizer to be dispersed varies with the method  
and purpose of dispersing, the average particle diameter  
15 thereof is 1.5  $\mu\text{m}$  or less, preferably 0.8  $\mu\text{m}$  or less. The  
particle size of the dispersed acid former and/or  
sensitizer <sup>is</sup> ~~has~~ <sup>ed</sup> distribution. Therefore, photosensitivity  
is expressed even when the average particle diameter is,  
for example, 1.0  $\mu\text{m}$  because of the presence of finer  
20 particles. If desired, after fully pulverizing and finely  
dispersing the acid former and/or sensitizer in an aqueous  
solution of <sup>the</sup> ~~a~~ water-soluble resin, large particles of the  
acid former and/or sensitizer may be removed by  
centrifugal separation or by filtration with a glass  
25 filter or a membrane filter, etc. It is known that a  
transparent coloring agent is obtainable by removing the  
pigment particles having greater than a certain particle  
size, as described in Japanese Unexamined Patent  
Publication No. S60-129707. In the case of the present  
30 invention, <sup>also</sup> ~~too~~, a photosensitive composition in which the  
light scattering effect is remarkably reduced can be  
obtained by removing large particles of the photo-acid  
former and sensitizer.

[0071] It is desirable to add an antifoaming agent  
35 during or after the ~~finely~~ <sup>2.5</sup> dispersing the acid former

and/or sensitizer in an aqueous solution of <sup>the</sup> ~~a~~ water-soluble resin. As the antifoaming agent suitable for the photosensitive composition of the present invention, there may be used antifoaming agents of a silicone-type and, additionally, antifoaming agents of an alcohol-type, an ether-type, a metallic soap-type, an ester-type and a higher fatty acid-type, as described in "Application of Antifoaming Agent", Tsunetaka SASAKI (editorial <sup>at</sup> ~~supervision~~), CMC (1991).

10 [0072] ~~To~~ <sup>the</sup> thus obtained composition may be further added with a water-soluble binder resin to ~~control~~ <sup>adjust a</sup> the properties, such as viscosity, of the photosensitive composition and to improve the properties of ~~the~~ <sup>the</sup> photosensitive film, such as mechanical strength, sensitivity and water resistance. As the binder resin, the water-soluble resin used as a dispersant can be used. It is desirable that the resin have a high polymerization ~~degree.~~ <sup>degree of</sup>

20 [0073] ~~In~~ <sup>the</sup> the formulation of the photosensitive composition of the present invention ~~is such that~~ the amount of the acid-reactive insolubilizing agent is 5 to 1,000 parts, preferably 10 to 500 parts, per 100 parts of the water-soluble resin serving as a dispersant and a binder resin; the amount of the acid former is 1 to 100 parts, preferably 5 to 50 parts, per 100 parts of the acid-reactive insolubilizing agent; the amount of the sensitizer is 5 to 100 parts, preferably 10 to 50 parts, per 100 parts of the acid former; and the total amount of these ingredients is 5 to 400 parts, preferably 10 to 200 parts, per 100 parts of water. When the amount of the acid former and the acid-reactive insolubilizing agent is less than the above ranges, sufficient photo-insolubilization does not occur, while the photo-insolubilization rate will not change even when the amounts thereof increase beyond the above ranges. When

35

the amount of the sensitizer is less than the above range, sufficient sensitization effect is not obtainable. Even when the <sup>amount of</sup> sensitizer ~~is~~ added <sup>9.5</sup> beyond ~~the~~ <sup>the foregoing</sup> above range, the sensitization rate does not increase, but ~~rather~~ the light transmittance is undesirably reduced.

[0074] ~~to~~ the photosensitive composition of the present invention, ~~a~~ finely dispersed extender such as aluminum oxide, silicon oxide, titanium oxide or zinc white may be added. An organic pigment which does not <sup>have</sup> give a sensitization effect <sup>on</sup> to the acid former, such as a copper, nickel or iron complex of phthalocyanine, may also be added thereto.

[0075] ~~to~~ the photosensitive composition of the present invention, ~~a~~ an aqueous resin emulsion the containing a dispersoid of hydrophobic polymer particles can be added. ~~As the hydrophobic polymer which constitutes~~ <sup>of</sup> such an aqueous resin emulsion, ~~there may be used~~ poly(vinyl acetate), a polyvinyl acetate/ethylene polymer, a polyvinyl acetate/acrylic ester polymer, a styrene/butadiene copolymer, a methyl methacrylate/butadiene copolymer, an acrylonitrile/butadiene copolymer, a chloroprene copolymer, an isoprene copolymer, a poly(meth)acrylic resin, polyurethane, a polyester resin, poly(vinyl chloride), poly(vinylidene chloride), polystyrene, a silicone resin, polyethylene, a fluororesin, etc. These resin emulsions are used in an amount of 0.05 to 5 parts, preferably 0.1 to 3 parts, per 1 part of the water-soluble resin.

[0076] The photosensitive composition of the present invention is suitable for forming a coating (resin film) on any substrate such as wood; textiles; paper; ceramics; glass; a synthetic resin, e.g. polyester, polyolefin, cellulose acetate, polyimide and epoxy resin; glass fiber reinforced resin; a metal, e.g. aluminum, copper, nickel, iron, zinc, magnesium and cobalt; a semiconductor material,

e.g. silicon and gallium-arsenide-germanium; and an insulating material, e.g. silicon nitride and silicon oxide. It is desirable that the substrate be <sup>imported with</sup> ~~subjected to~~ hydrophilicity ~~imparting treatment~~ beforehand especially in the case of synthetic resin, for the purpose of improving the film forming efficiency, thereof. A pattern or a protective layer may be formed by irradiating the coating, made of the photosensitive composition of the present invention and formed on these substrates, with light.

[0077] The composition may be applied on a surface of the substrate by any known method capable of forming an uniform coating, such as by <sup>roller application</sup> ~~rotation coating~~, brushing, spraying, reverse roll coating, ~~dip coating~~, doctor knife coating or curtain coating. The <sup>average</sup> ~~thickness~~ of the film may range from 0.1  $\mu\text{m}$  to 1,000  $\mu\text{m}$  ~~in terms of average thickness~~, though the thickness is dependent on the <sup>intended application type</sup> ~~purpose~~, on the ~~kind of the~~ substrate and on the particle size of the acid former or sensitizer.

[0078] The photosensitive composition applied on the substrate is exposed to light after evaporating <sup>ion of the</sup> ~~water~~. The sensitization wavelength region is determined by the <sup>type</sup> ~~kind~~ of the acid former and the sensitizer. Since a wide range of sensitizers can be used, the <sup>utilizable</sup> ~~wavelength of light~~ ranges from far ultraviolet ~~ray region to an infrared region~~. <sup>suitable</sup> ~~As the light source, there may be suitably used~~ low pressure mercury lamp, a high pressure mercury lamp, a super-high pressure mercury lamp, a xenon lamp, a mercury-xenon lamp, a halogen lamp, a fluorescent lamp and ~~also~~ various laser light sources which oscillate ultraviolet <sup>or radiation</sup> ~~rays~~, visible ~~ray~~ and infrared ~~rays~~. The exposure may be ~~done~~ through a photo mask. Alternatively, the photosensitive film may be directly <sup>patterned using a</sup> ~~written with~~ laser beam. Furthermore, <sup>also utilize</sup> ~~it is without saying that the~~ exposure can be carried out using activation energy rays such as

electron beams <sup>or</sup> and X-rays.

- [0079] The <sup>portion (s) of the</sup> photosensitive film which has been <sup>exposed</sup> ~~subjected~~ to light <sup>becomes</sup> ~~exposure is~~ insoluble in water. To facilitate ~~the~~ insolubilization, the light exposure may be followed
- 5 by a heat treatment. The temperature used in the heat treatment may vary depending upon the <sup>type</sup> ~~kind~~ of the substrate but is generally in the range from room temperature to 250°C, preferably in the range from room temperature to 150°C. The heat treatment time depends
- 10 upon the <sup>type</sup> ~~kind~~ of the photosensitive composition and heating temperature, but is <sup>within the range of</sup> 30 seconds to 60 minutes.
- [0080] The film which has been <sup>exposed</sup> ~~subjected~~ to the light ~~exposure~~ and, if necessary, ~~the~~ heat treatment, is developed with neutral water. The development may be
- 15 ~~achieved~~ by immersing the photosensitive film in water for ~~the~~ dissolution and removal of the unexposed area or by contacting <sup>with a spray</sup> ~~water flows~~ from a spray gun for the removal of the unexposed area.
- [0081] A screen printing plate may be prepared by a
- 20 conventional method which includes applying the photosensitive composition of the present invention over a screen, followed by drying, light exposure and development. Alternatively, a screen printing plate may ~~also~~ be prepared by a conventional method which includes applying
- 25 the photosensitive composition on a plastic film, drying the coating to obtain a photosensitive film ~~for preparing a screen printing plate~~, applying the film on a screen plate using water, etc., drying the assembly, removing the plastic film, followed by light exposure and development.
- 30 [0082] Further, the <sup>radiation</sup> ~~activation energy ray~~-sensitive composition of the present invention may be used as an aqueous coating material. Thus, the composition is applied on a surface of a substrate, the coating being irradiated with ultraviolet ~~rays~~, visible light, <sup>or</sup> near
- 35 infrared <sup>radiation</sup> ~~rays~~ or an electron beam to harden the surface.

~~Industrial Applicability:~~

- [0083] Since <sup>radiation</sup> the activation energy ray-sensitive composition <sup>of</sup> ~~an activation energy ray-sensitive film~~ obtainable from the composition and a pattern forming method according to the present invention <sup>offers the following</sup> ~~have the above-described constitution, the following effects are obtained.~~
- [0084] (1) Since only water is used as a solvent for preparation of the <sup>radiation</sup> activation energy ray-sensitive composition and for <sup>its</sup> development <sup>is</sup> ~~treatment~~, the composition ~~is suited for ensuring~~ the safety of work environment, fire prevention, prevention of pollution, etc.
- [0085] (2) Since the acid former can generate an acid, not only by the action of light, but also by the action of <sup>forms</sup> activation energy ~~rays~~ such as electron beams or X-rays, ~~the composition is not only sensitive to light but also sensitive to electron beams and X-rays.~~
- [0086] (3) Since various sensitizers can be used together, the composition obtained may be sensitive to <sup>spectrum of</sup> ~~rays~~ of a wide wavelength <sup>the</sup> ranging from the far ultraviolet ray region to <sup>a</sup> near infrared ~~ray region.~~
- [0087] (4) The composition can be applied to a film or a screen substrate to form <sup>a radiation</sup> ~~an activation energy ray-sensitive film~~ which serves as a photosensitive film <sup>term storage.</sup> capable of ~~storing for a long period of time.~~
- [0088] (5) A pattern of high resolution can be obtained by <sup>utilizing a small</sup> ~~adjusting the~~ particle size of the water-insoluble or sparingly water-soluble acid former and <sup>of</sup> ~~the sensitizer, to a small size.~~
- [0089] (6) The composition can provide a surface coating ~~material~~ hardenable by light exposure or electron beam irradiation.
- [0090] (7) The <sup>radiation</sup> ~~activation energy ray-sensitive~~ composition and a film obtainable therefrom ~~are~~ <sup>can be</sup> advantageously utilized in the field of printing such as



screen printing platemaking and also advantageously used as a coating composition, an adhesive composition, etc.

Examples:

- 5 [0091] The present invention will ~~be next described in further detail by~~ <sup>working</sup> examples. *illustrated*

Examples 1 to 12

- 10 [0092] Preparation of Dispersions of Photo-Acid Former and Sensitizer:

[0093] A dispersion of a photo-acid former was prepared using a planetary-type fine pulverizer (Model P-7 manufactured by Fritsch Inc., Germany) and 45 mL pulverizing vessel made of stainless steel or zirconia in 15 the following manner.

[0094] Poly(vinyl alcohol) (PVA, manufactured by Nihon Gosei Kagaku Co., Ltd.) as a dispersant was dissolved in water to obtain a 15% by weight aqueous solution. The aqueous solution (15 mL) and a photo-acid former and/or 20 sensitizer were charged in the pulverizing vessel, to which about 15 mL of stainless steel or zirconia pulverizing beads, having a diameter of 5/32 inches and made of the same material as that of the pulverizing vessel and an antifoaming agent (AQUAREN 1488 manufactured 25 by Kyoeisha) were added. The vessel was closed and rotated at a ~~revolution~~ speed of 500 rpm for 5 minutes in one direction. Such a pulverization treatment was performed 4 times in total while alternately changing the rotational direction. Thereafter, the pulverizing beads 30 were removed by filtration to obtain a photosensitive dispersion. The thus obtained photosensitive dispersions were as shown in Table 1. The average particle diameter of the fine particles in the dispersions was 0.51 to 0.72  $\mu\text{m}$ .

Table 1

Preparation of Dispersions of Photo-Acid Former and Sensitizer

Example	Dispersant: PVA solution	Photo-acid former and Amount added	Sensitizer and Amount added
1	10 parts by weight	Tribromomethylphenyl sulfone: 4 parts by weight	
2	10 parts by weight	Bis(tert-phenyl)iodonium hexafluorophosphate: 4 parts by weight	
3	10 parts by weight	3-Methoxyphenylamine-4-diazonium hexafluorophosphate: 4 parts by weight	
4	10 parts by weight	2-(p-methoxyphenyl)4,6-bis(trichloromethyl)triazine: 4 parts by weight	
5	10 parts by weight	2-{2-(p-methoxyphenyl)ethenyl}4,6- bis(trichloromethyl)triazine: 4 parts by weight	
6	10 parts by weight	Dimethylphenacyl phosphonium tetra(pentafluorophenyl)borate: 4 parts by weight	
7	10 parts by weight		2-chlorothioxanthone: 1 part
8	10 parts by weight	Tribromomethylphenyl sulfone: 4 parts by weight	9,10-dieethoxyanthracene: 1 part by weight
9	10 parts by weight	Tribromomethylphenyl sulfone: 4 parts by weight	Bis(p-diethylamino)benzophenone: 1 part by weight
10	10 parts by weight	Tribromomethylphenyl sulfone: 4 parts by weight	3,3-Carbonylbis(7-diethylaminocoumarin): 1 part by weight
11	10 parts by weight	Tribromomethylphenyl sulfone: 4 parts by weight	2-Chlorothioxanthone: 1 part by weight
12	10 parts by weight	Bis(tert-phenyl)iodonium hexafluorophosphate: 4 parts by weight	3,3-Carbonylbis(7-diethylaminocoumarin): 1 part by weight

Examples 13 to 56

[0095] Preparation of Photosensitive Compositions:

[0096] While stirring the dispersion of the photo-acid former or sensitizer obtained in each of Examples 1 to 12, 5 an acid-reactive insolubilizing agent and an aqueous solution of a binder resin were added thereto. <sup>used was</sup> ~~As the~~ acid-reactive insolubilizing agent, ~~N~~-methylolacrylamide (manufactured by Soken Chemical Co., Ltd.), methylolmelamine (M-3, manufactured by Sumitomo Chemical 10 Co., Ltd.), resol resin (RESITOP PL-4668, manufactured by Gun-ei Chemical Industry Co., Ltd.), methylolated urea (EX-211 or EX-321, manufactured by Nagase Chemtex Inc.) or an oxetane compound (OXT-121, manufactured by Toa Gosei Co., Ltd.), ~~was used~~. As an acrylic monomer, ethylene 15 glycol diacrylate (PET-30, manufactured by Nippon Kayaku Co., Ltd.) was used. As the binder resin, a 15 % by weight aqueous solution of K-217 (manufactured by Kuraray Co., Ltd) or a 10 % by weight aqueous solution of poly(vinyl alcohol) (PVA-SbQ) containing 1.4 mole % 20 stilbazolium substituent was used. As a resin emulsion, HA-100 manufactured by Clariant Polymer Co., Ltd. was used. To each of these photosensitive compositions, FL-GB blue (manufactured by Dainichiseika Kogyo Co., Ltd.) was added. The thus obtained photosensitive compositions were as 25 shown in Tables 2 to 5.

Table 2 Preparation of Photosensitive Compositions

Example	Photo-acid former dispersion	Acid-reactive insolubilizing agent	Binder resin
13	Sample of Example 1: 1 part by weight Sample of Example 7: 1 part by weight	N-methyloxyacrylamide: 1.5 parts by weight	K-217Aqueous solution: 100 parts by weight
14	Sample of Example 1: 1 part by weight Sample of Example 7: 1 part by weight	Methyloxy melamine: 1.5 parts by weight	K-217Aqueous solution: 100 parts by weight
15	Sample of Example 1: 1 part by weight Sample of Example 7: 1 part by weight	Methyloxy urea: 1.5 parts by weight	K-217Aqueous solution: 100 parts by weight
16	Sample of Example 1: 1 part by weight Sample of Example 7: 1 part by weight	Resol resin: 1.5 parts by weight	K-217Aqueous solution: 100 parts by weight
17	Sample of Example 1: 1 part by weight Sample of Example 7: 1 part by weight	N-methyloxy acrylamide: 1.5 parts by weight	Aqueous solution of PVA-StO: 10 parts by weight
18	Sample of Example 2: 1 part by weight Sample of Example 7: 1 part by weight	N-methyloxy acrylamide: 1.5 parts by weight	K-217Aqueous solution: 100 parts by weight
19	Sample of Example 2: 1 part by weight Sample of Example 7: 1 part by weight	Methyloxy urea: 1.5 parts by weight	K-217Aqueous solution: 100 parts by weight
20	Sample of Example 2: 1 part by weight Sample of Example 7: 1 part by weight	Resol resin: 1.5 parts by weight	K-217Aqueous solution: 100 parts by weight

[00971] Table 3 Preparation of Photosensitive Compositions

Example	Photo-acid former dispersion	Acid-reactive insolubilizing agent	Binder resin
21	Sample of Example 2: 1 part by weight	Epoxy compound: 40 parts by weight	K-217Aqueous solution:
	Sample of Example 7: 1 part by weight	Oxetane compound: 10 parts by weight	100 parts by weight
22	Sample of Example 3: 1 part by weight	N-methylolacrylamide: 1.5 parts by weight	K-217Aqueous solution:
			100 parts by weight
23	Sample of Example 3: 1 part by weight	Methylol melamine: 1.5 parts by weight	K-217Aqueous solution:
			100 parts by weight
24	Sample of Example 3: 1 part by weight	Methylolated urea: 1.5 parts by weight	K-217Aqueous solution:
			100 parts by weight
25	Sample of Example 3: 1 part by weight	Resol resin: 1.5 parts by weight	K-217Aqueous solution:
			100 parts by weight
26	Sample of Example 3: 1 part by weight	Epoxy compound: 40 parts by weight	K-217Aqueous solution:
			100 parts by weight
27	Sample of Example 3: 1 part by weight	N-methylol acrylamide: 1.5 parts by weight	K-217Aqueous solution:
		Terephthalaldehyde bisdiethyl acetal:	
		1.5 parts by weight	100 parts by weight
28	Sample of Example 4: 1 part by weight	N-methylol acrylamide: 1.5 parts by weight	K-217Aqueous solution:
			100 parts by weight
29	Sample of Example 4: 1 part by weight	Methylol melamine: 1.5 parts by weight	K-217Aqueous solution:
			100 parts by weight
30	Sample of Example 4: 1 part by weight	Methylolated urea: 1.5 parts by weight	K-217Aqueous solution:
			100 parts by weight
31	Sample of Example 4: 1 part by weight	Resol resin: 1.5 parts by weight	K-217Aqueous solution:
			100 parts by weight
32	Sample of Example 5: 1 part by weight	N-methylol acrylamide: 1.5 parts by weight	K-217Aqueous solution:
			100 parts by weight
33	Sample of Example 5: 1 part by weight	Methylol melamine: 1.5 parts by weight	K-217Aqueous solution:
			100 parts by weight
34	Sample of Example 5: 1 part by weight	Methylol melamine: 1.5 parts by weight	K-217Aqueous solution:
		Pentaerythritol acrylate: 1.5 parts by weight	100 parts by weight
35	Sample of Example 5: 1 part by weight	Resol resin: 1.5 parts by weight	K-217Aqueous solution:
			100 parts by weight

[0098]

Table 4 Preparation of Photosensitive Compositions

Example	Photo-acid former dispersion	Acid-reactive insolubilizing agent	Binder resin
36	Sample of Example 6: 1 part by weight	N-methylol acrylamide: 1.5 parts by weight Diethylene glycol diacrylate: 1.5 parts by weight	K-217Aqueous solution:100 parts by weight
37	Sample of Example 6: 1 part by weight	Resol resin: 1.5 parts by weight	K-217Aqueous solution:100 parts by weight
38	Sample of Example 6: 1 part by weight	Epoxy compound: 40 parts by weight	K-217Aqueous solution:100 parts by weight
39	Sample of Example 8: 1 part by weight	N-methylol acrylamide: 1.5 parts by weight	K-217Aqueous solution:100 parts by weight
40	Sample of Example 8: 1 part by weight	Methylolated urea: 1.5 parts by weight	K-217Aqueous solution:100 parts by weight
41	Sample of Example 9: 1 part by weight	Methylolated urea: 1.5 parts by weight	K-217Aqueous solution:100 parts by weight
42	Sample of Example 9: 1 part by weight	Resol resin: 1.5 parts by weight	K-217Aqueous solution:100 parts by weight
43	Sample of Example 10: 1 part by weight	N-methylol acrylamide: 1.5 parts by weight	K-217Aqueous solution:100 parts by weight
44	Sample of Example 10: 1 part by weight	Methylolated urea: 1.5 parts by weight	K-217Aqueous solution:100 parts by weight
45	Sample of Example 11: 1 part by weight	N-methylol acrylamide: 1.5 parts by weight	K-217Aqueous solution:100 parts by weight
46	Sample of Example 11: 1 part by weight	Resol resin: 1.5 parts by weight	K-217Aqueous solution:100 parts by weight
47	Sample of Example 12: 1 part by weight	N-methylol acrylamide: 1.5 parts by weight	K-217Aqueous solution:100 parts by weight
48	Sample of Example 12: 1 part by weight	Methylol melamine: 1.5 parts by weight	K-217Aqueous solution:100 parts by weight
49	Sample of Example 12: 1 part by weight	Resol resin: 1.5 parts by weight	K-217Aqueous solution:100 parts by weight
50	Sample of Example 12: 1 part by weight	Epoxy compound: 40 parts by weight	K-217Aqueous solution:100 parts by weight
51	Sample of Example 12: 1 part by weight	Epoxy compound: 20 parts by weight Diethylene glycol diacrylate: 20 parts by weight	K-217Aqueous solution:100 parts by weight

[0099] Table 5

Example	Photo-acid former dispersion	Acid-reactive insolubilizing agent	Resin emulsion	Binder resin
52	Sample of Example 8: 1 part by weight	N-methylol acrylamide: 1.5 parts by weight	HA-10: 15 parts By weight	K-217Aqueous solution: 100 parts by weight
53	Sample of Example 8: 1 part by weight	Methylolated urea: 1.5 parts by weight	HA-10: 15 parts By weight	K-217Aqueous solution: 100 parts by weight
54	Sample of Example 8: 1 part by weight	Resol resin: 1.5 parts by weight	HA-10: 15 parts By weight	K-217Aqueous solution: 100 parts by weight
55	Sample of Example 9: 1 part by weight	N-methylol acrylamide: 1.5 parts by weight	HA-10: 15 parts By weight	K-217Aqueous solution: 100 parts by weight
56	Sample of Example 10: 1 part by weight	Methylol melamine: 1.5 parts by weight	HA-10: 15 parts By weight	K-217Aqueous solution: 100 parts by weight

Comparative Examples 1 to 4

[0100]

- 5            Photosensitive compositions prepared without using the acid-reactive insolubilizing agent or using only a radically polymerizable monomer are shown in Table 6 as comparative examples.

10 Table 6 Preparation of Photosensitive Films

Comparative Example	Photo-acid former dispersion	Additive	Binder resin
1	Sample of Example 3: 1 part by weight	None	K-217Aqueous solution: 100 parts by weight
2	Sample of Example 3: 1 part by weight	Diethylene glycol diacrylate: 15 parts by weight	K-217Aqueous solution: 100 parts by weight
3	Sample of Example 8: 1 part by weight	Diethylene glycol diacrylate: 20 parts by weight	K-217Aqueous solution: 100 parts by weight
4	Sample of Example 10: 1 part by weight	Diethylene glycol diacrylate: 20 parts by weight	K-217Aqueous solution: 100 parts by weight

Examples 57 to 104

**[0101]**     Preparation of Photosensitive Films and  
Photosensitization Characteristics:

**[0102]**     The photosensitive compositions obtained in  
5   Examples 13 to 56 were each applied onto a polyester film.  
The coatings were dried at 40°C for 15 minutes to obtain  
photosensitive films having thicknesses of 25 to 30 µm.  
Each film was irradiated through a photomask placed in  
contact therewith using a 4 KW high pressure mercury lamp  
10   or a 3 KW halogen lamp spaced a distance of 1 m ~~away~~ ✓  
therefrom. After irradiation, water was sprayed thereon  
using a spray gun to effect development. Prior to the  
development with water, a heat treatment was carried out  
for given temperature and time, when needed. The results  
15   are summarized in Tables 7 and 8, in which the evaluation  
of image formation is rated as follows:

**[0103]**     yes: negative pattern is obtained

**[0104]**     no: pattern is not formed

**[0105]**     Good patterns were obtained when the acid-  
20   reactive insolubilizing agent was used. When no acid-  
reactive insolubilizing agent was added or when only a  
radically polymerizable monomer was added, negative  
patterns were not obtained. ✓



Table 7 Photosensitization Characteristics of Films  
obtained from Photosensitive Compositions

Example	Photosensitive Composition Preparation Example	Light Source	Exposure Time (min.)	Heat treatment condition	Image formation
57	Example 13	Mercury lamp	3	80°C, 10 minutes	A
58	Example 14	Mercury lamp	3	80°C, 10 minutes	A
59	Example 15	Mercury lamp	3	40°C, 20 minutes	A
60	Example 16	Mercury lamp	3	40°C, 20 minutes	A
61	Example 17	Mercury lamp	2	40°C, 20 minutes	A
62	Example 18	Halogen lamp	3	40°C, 20 minutes	A
63	Example 19	Halogen lamp	3	40°C, 20 minutes	A
64	Example 20	Halogen lamp	3	40°C, 20 minutes	A
65	Example 21	Halogen lamp	3	Room temperature 120 minutes	A
66	Example 22	Mercury lamp	2.5	80°C, 10 minutes	A
67	Example 23	Mercury lamp	2.5	80°C, 10 minutes	A
68	Example 24	Mercury lamp	2.5	40°C, 20 minutes	A
69	Example 25	Mercury lamp	2.5	40°C, 20 minutes	A
70	Example 26	Mercury lamp	2.5	40°C, 20 minutes	A
71	Example 27	Mercury lamp	2.5	40°C, 20 minutes	A
72	Example 28	Mercury lamp	4	80°C, 5 minutes	A
73	Example 29	Mercury lamp	3	80°C, 5 minutes	A
74	Example 30	Mercury lamp	3	80°C, 5 minutes	A
75	Example 31	Mercury lamp	3	80°C, 5 minutes	A
76	Example 32	Mercury lamp	3	80°C, 5 minutes	A
77	Example 33	Mercury lamp	2.5	80°C, 5 minutes	A
78	Example 34	Mercury lamp	2.5	80°C, 5 minutes	A
79	Example 35	Mercury lamp	2.5	40°C, 20 minutes	A
80	Example 36	Mercury lamp	1	40°C, 20 minutes	A

[0106]

Table 8 Photosensitization Characteristics of Films obtained from Photosensitive Compositions

Example	Photosensitive Composition Preparation Example	Light Source	Exposure Time (min.)	Heat treatment condition	Image formation
81	Example 37	Mercury lamp	2.5	40°C, 20 minutes	A
82	Example 38	Mercury lamp	2	40°C, 20 minutes	A
83	Example 39	Halogen lamp	2	40°C, 20 minutes	A
84	Example 40	Halogen lamp	2	40°C, 20 minutes	A
85	Example 41	Halogen lamp	1.5	80°C, 20 minutes	A
86	Example 42	Halogen lamp	1.5	40°C, 20 minutes	A
87	Example 43	Halogen lamp	1.5	40°C, 20 minutes	A
88	Example 44	Halogen lamp	1	Room temperature 120 minutes	A
89	Example 45	Mercury lamp	3	40°C, 20 minutes	A
90	Example 46	Mercury lamp	3	40°C, 20 minutes	A
91	Example 47	Mercury lamp	1	40°C, 20 minutes	A
92	Example 48	Mercury lamp	1	80°C, 10 minutes	A
93	Example 49	Mercury lamp	1	80°C, 10 minutes	A
94	Example 50	Mercury lamp	1	40°C, 20 minutes	A
95	Example 51	Mercury lamp	1	40°C, 20 minutes	A
96	Example 52	Mercury lamp	2	40°C, 20 minutes	A
97	Example 53	Mercury lamp	2	80°C, 10 minutes	A
98	Example 54	Mercury lamp	2	80°C, 10 minutes	A
99	Example 55	Mercury lamp	1.5	40°C, 20 minutes	A
100	Example 56	Mercury lamp	1	40°C, 20 minutes	A
101	Comparative Example 1	Mercury lamp	10	40°C, 20 minutes	B
102	Comparative Example 2	Mercury lamp	5	40°C, 20 minutes	B
103	Comparative Example 3	Mercury lamp	10	40°C, 20 minutes	B
104	Comparative Example 4	Mercury lamp	5	80°C, 10 minutes	B

5 Examples 105 to 117

[0107] Preparation of Films for Screen Platemaking and Photosensitization Characteristics:

[0108] The photosensitive compositions obtained in the above examples were each applied onto a 250 mesh polyester screen and then dried. Such application and drying

operations were repeated to obtain uniform films having thicknesses of about 15  $\mu$ m. Each film was irradiated through a photomask placed in contact therewith using a 4 KW high pressure mercury lamp or a 3 KW halogen lamp spaced a distance of 1 m ~~away~~ therefrom. After irradiation, water was sprayed thereon using a spray gun to effect development. Prior to the development with water, a heat treatment was carried out for given temperature and time, when needed. The results are shown in Table 9. The patterns obtained exhibited good water resistance and show good resistance against organic solvents such as toluene, acetone, ethyl acetate and butyl cellosolve. When the compositions of Comparative Examples were used, however, patterns were not formed by water development after ~~the~~ exposure.

Table 9 Sensitization Characteristics of Films for Screen Platemaking obtained from Photosensitive Composition

Example	Photosensitive Composition Preparation Example	Light Source	Exposure Time (min.)	Heat treatment condition	Image Formation	Water Resistance	Solvent resistance
105	Example 13	Mercury lamp	3	40°C, 20 minutes	A	A	A
106	Example 21	Mercury lamp	3	40°C, 20 minutes	A	A	A
107	Example 22	Mercury lamp	3	40°C, 20 minutes	A	A	A
108	Example 26	Mercury lamp	4	40°C, 30 minutes	A	A	A
109	Example 28	Mercury lamp	1	40°C, 20 minutes	A	A	A
110	Example 36	Mercury lamp	2	40°C, 20 minutes	A	A	A
111	Example 38	Mercury lamp	2	40°C, 20 minutes	A	A	A
112	Example 42	Mercury lamp	1.5	40°C, 20 minutes	A	A	A
113	Example 50	Mercury lamp	2	40°C, 30 minutes	A	A	A
114	Example 51	Mercury lamp	2	40°C, 30 minutes	A	A	A
115	Example 52	Mercury lamp	1.5	40°C, 20 minutes	A	A	A
116	Comp. Example 1	Mercury lamp	10	40°C, 20 minutes	B	B	B
117	Comp. Example 1	Mercury lamp	10	40°C, 20 minutes	B	B	B

ABSTRACT

<sup>A radiation</sup>  
~~An activation energy ray-sensitive composition which can be~~  
~~permitting development with neutral water. Provided is an~~  
~~activation energy ray-sensitive composition characterized~~  
5 ~~by comprising a dispersion which comprises~~ <sup>is provided as</sup> an aqueous  
solution of a water-soluble resin, and an acid former  
~~dispersed in the aqueous solution~~ <sup>therein</sup> in the form of fine  
powder. <sup>is</sup> The acid former being insoluble or sparingly  
soluble in water and generating <sup>es</sup> an acid by ~~the action of~~ <sup>radiation</sup>  
10 ~~activation energy rays, and an acid-reactive~~  
insolubilizing agent <sup>is</sup> dissolved or dispersed in the  
dispersion and <sup>converts</sup> insolubilizing the water-soluble resin <sup>into an</sup>  
~~insoluble form in the presence of an~~  
~~the action of the acid.~~